Claim Amendments

CLAIMS:

- 1. (Currently Amended) A process for extracting a metal from a refractory material containing the metal, the process comprising fine grinding the material, subjecting the ground material to a leaching step <u>carried out at 1 atmosphere or less</u> in the presence of an alkaline material and an oxidizing agent, adjusting the leaching step <u>such that to produce partially oxidized material</u>, wherein the amount of oxidation <u>of the partially oxidized material</u> is between 9%-20%, and subjecting the partially oxidized material to a cyanide extraction step to recover the metal.
- 2. (Original) The process of claim 1, wherein the refractory material comprises a sulphide, a carbonaceous, a pyrite, an arsenopyrite, or a stibnite ore or concentrate.
- 3. (Original) The process of claim 1, wherein the material is ground to a p80 of <20 microns.
- 4. (Original) The process of claim 1, wherein the alkaline material is selected from lime and limestone.
- 5. (Original) The process of claim 4, wherein the pH of the leaching step is between 5-7.
- 6. (Original) The process of claim 1, wherein the amount of oxidation is between about 9% to about 12%.
 - 7. (Original) The process of claim 1, wherein the oxidizing agent is oxygen.
- 8. (Currently Amended) The process of claim 1, wherein the leaching step is conducted at a temperature of between 60°C - 95°C .
 - 9. (Cancelled)

- 10. (Original) The process of claim 1, wherein the metal is gold or silver.
- 11. (Original) A process for extracting gold or silver from a refractory material containing gold or silver, the process comprising fine grinding the material to a p80 of <20 microns, subjecting the ground material to a leaching step in the presence of an alkaline material which comprises lime and/or limestone and an oxidizing agent which comprises oxygen, maintaining the pH of the leaching step between 5-7, maintaining the temperature between 60-85 degrees C, adjusting the leaching step such that the amount of oxidation is between about 9%-about 12%, and subjecting the partially oxidized material to a cyanide extraction step to recover the gold or silver.